

Technical Data Sheet - PA15-PE80 Film for Fresh Pasta

Source document: S4_Scheda_tecnica_pasta_fresca.pdf

Parameter	Value
Issue date	23 April 2026
Customer	Casa Prencipe di Prencipe Domenico & Armillotta Giovanna SNC
Product	Neutral and printed laminated film PA15-PE80
Basis weight	81.5 g/m ² ; tolerance 3 g/m ² / 6%
Web width	455 mm
Dynamic COF, internal/internal	0.25 +/-0.02 (ASTM D 1894-01)
Dynamic COF, internal/external	0.35 +/-0.02 (ASTM D 1894-01)
Oxygen permeability	<2.4 cm ³ /m ² /24h, OTR 23 deg C - 0% RH (ASTM D 3985)*
Water-vapour permeability	<7.85 g/m ² /24h, WVTR 38 deg C - 90% RH (ASTM F 1249)*

* Indicative values estimated on the basis of the average base-film structure.

Supplier: Silvano Plast, Via Barletta 256, 76123 Andria (BT), Italy - VAT no. 04937690727.